

an EnPro Industries company





MATERIAL PROPERTIES

Color: Off White Composition: PTFE with barium sulfate Fluid Services¹: Strong caustics, moderate acids, chlorine, gases, water, steam, cryogenics, hydrocarbons and aluminum fluoride Temperature², °F (°C) Minimum: -450 (-268) Continuous Max: +500 (+260) Pressure², Maximum, psig (bar): 1200 (83) P x T (max.)², psig x °F (bar x °C) 1/32 and 1/16": 350,000 (12,000) 1/8": 250,000 (8,600) Flammability: Will Not Burn

ABS (American Bureau of Shipping) and FDA (Food and Drug Administration)

Will Not Support

TYPICAL PHYSICAL PROPERTIES*

Meets Specification:

Bacterial Growth:

| ASTM F36 | Compressibility, %: | 4 | -10 | |
|-------------------|--|-----------------------------------|---------------------------------|--|
| ASTM F36 | Recovery, %: | 4 | 40 | |
| ASTM F38 | Creep Relaxation, %: | 11 | | |
| ASTM F152 | Tensile, Across Grain, psi (N/mm²): | 2000 (13.8) | | |
| ASTM D792 | Specific Gravity: | 2.80 | | |
| ASTM D1708 | Modulus @ 100% Elongation, psi (N/mm2): | 1400 (9.6) | | |
| ASTM F433 | Thermal Conductivity (K), W/m°K (Btu.·in./hr.·ft. ² ·°F): | 0.29-0.38 (2.00-2.65) | | |
| ASTM D149 | Dielectric Properties, range, volts/mil. | | | |
| | Sample conditioning | <u>1/16"</u> | <u>1/8"</u> | |
| | 3 hours at 250°F: | 466 ⁽³⁾ | - | |
| | 96 hours at 100% Relative Humidity | 59 | - | |
| ASTM F586 | Design Factors | <u>1/16" & Under</u> | <u>1/8"</u> | |
| | "m" factor: | 2.0 | 2.0 | |
| | "y" factor, psi (N/mm²): | 2350 (16.2) | 2500 (17.2) | |
| ROTT | Gasket Constants, 1/16": | Gb=289 a= | 0.274 Gs=6.61x10 ⁻¹¹ | |
| | 1/8": | Gb=444 a= | 0.332 Gs=1.29x10 ⁻² | |
| ASTM F104 | Line Call Out: | F451999A9B2E99K5M6 ⁽⁴⁾ | | |

SEALING CHARACTERISTICS

| | ASTM F37B | DIN 3535- 4 |
|--------------------------------|-------------|------------------|
| | Fuel A | Gas Permeability |
| Gasket Load, psi (N/mm2): | 1000 (7) | 4640 (32) |
| Internal Pressure, psig (bar): | 9.8 (0.7) | 580 (40) |
| Leakage | 0.04 ml/hr. | <0.015 cc/min |

Notes

This is a general guide and should not be the sole means of selecting or rejecting this material. ASTM test results in accordance with ASTM F-104; properties based on 1/32" (0.8mm) sheet thickness unless otherwise mentioned.

^{*} Values do not constitute specification Limits

¹ See Garlock chemical resistance guide.

² Based on ANSI RF flanges at our preferred torque. When approaching maximum pressure, continuous operating temperature, minimum temperature or 50% of maximum PxT, consult Garlock Applications Engineering.

 $^{^{\}rm 3}$ Indicates current arced around and not through gasket. Dielectric higher than indicated.

⁴ Increase in IRM Oil #903 (fourth numeral 9 is thickness, fifth numeral 9 is weight): Thickness = 1.0% max, Weight = 2.0% max. Sixth numberal 9: % Increase in Water: Weight = 1.0% max. A9: Leakage in Fuel A (Isooctane), Pressure = 9.8psig (0.7bar), Gasket Load = 1,000psi (7.0N/mm2): Typical = 0.04ml/hr, Max = 1.0ml/hr. E99: % Increase in ASTM Fuel B: Weight: 2.0% max., Thickness: 1.0% max.