

an EnPro Industries company



# **Garlock OFF-WHITE GYLON® HP 3561**

## Metal Inserted GYLON 3510

#### MATERIAL PROPERTIES<sup>\*</sup>

Color:	Off-white		
Composition:	PTFE with barium sulfate and perforated 316L stainless steel insert		
Fluid Services <sup>1</sup> :	Strong caustics, moderate acids, chlorine, gases, water, steam, cyrogenics,		
	hydrocarbons and aluminum fluoride		
Temperature <sup>2</sup> , °F (°C)			
Continuous Max:	+500 (+260)		
Pressure <sup>2</sup> , Maximum, psig (bar):	2500 (172)		
<b>P x T (max.)</b> <sup>2</sup> , psig x °F (bar x °C)			
1/32 and 1/16":	700,000 (25,000)		
1/8":	450,000 (15,000)		
Flammability:	Will Not Burn		
Bacterial Growth:	Will Not Support		

#### **TYPICAL PHYSICAL PROPERTIES**

ASTM F36	Compressibility, %:	3-7 <sup>(3)</sup>	
ASTM F36	Recovery, %:	50 <sup>(3)</sup>	
ASTM F38	Creep Relaxation, %:	20 <sup>(3)</sup>	
ASTM F152	Tensile, Across Grain, psi (N/mm <sup>2</sup> ):	5000 (34) <sup>3</sup>	
ASTM D1708	Modulus @ 100% Elongation, psi (N/mm <sup>2</sup> ):	N/A	
ASTM F433	Thermal Conductivity (K), W/m°K (Btu.·in./hr.·ft. <sup>2</sup> ·°F):	0.29-0.38 (2.00-2.65)	
ASTM F586	Design Factors	<u>1/16" &amp; Under</u> <u>1/8"</u>	
	"m" factor:	5.0 5.0	
	"y" factor, psi (N/mm <sup>2</sup> ):	3500 (24.1) 4000 (27.6)	
ROTT	Gasket Constants, 1/16":	Gb=72.3 a=0.466 Gs=2.16x10 <sup>-1</sup>	
ASTM F104	Line Call Out:	F451999A9B2E99K5M6 <sup>(3,4)</sup>	

### SEALING CHARACTERISTICS<sup>\*</sup>

	ASTM F37B Fuel A	DIN 3535- 4 Gas Permeability
Gasket Load, psi (N/mm2):	1000 (7)	4640 (32)
Internal Pressure, psig (bar):	9.8 (0.7)	580 (40)
Leakage	0.01 <sup>(3)</sup> ml/hr.	<0.015 <sup>(3)</sup> cc/min

#### Notes:

This is a general guide and should not be the sole means of selecting or rejecting this material. ASTM test results in accordance with ASTM F-104; properties based on 1/16" (1.6mm) sheet thickness unless otherwise mentioned.

\* Values do not constitute specification Limits

<sup>1</sup> See Garlock chemical resistance guide.

<sup>2</sup> Based on ANSI RF flanges at our preferred torque. When approaching maximum pressure, continuous operating temperature, minimum temperature or 50% of maximum PxT, consult Garlock Applications Engineering.

<sup>3</sup> Tested on 1/16" thick material.

<sup>4</sup> Tested on 1/16" material. Increase in IRM Oil #903 (fourth numeral 9 is thickness, fifth numeral 9 is weight): Thickness = 1.0% max, Weight = 2.0% max. Sixth numberal 9: % Increase in Water: Weight = 1.0% max. A9: Leakage in Fuel A (Isooctane), Gasket Load = 1,000psi (7.0N/mm2), Pressure = 9.8psig (0.7bar): Typical = 0.04ml/hr, Max = 1.0ml/hr. E99: % Increase in ASTM Fuel B: Weight: 2.0% max., Thickness: 1.0% max.