

Technical Information—Rev. 8, June 2011

Product Description

DuPont[™] Kalrez[®] 8575 perfluoroelastomer parts are a white product for "select" etch, ash/strip and deposition process applications. It offers very low weight loss in oxygen and fluorine-based plasmas, low outgassing, and excellent elastic recovery properties. Kalrez[®] 8575 has excellent vacuum and long-term sealing performance, good mechanical properties and is well-suited for both static and dynamic sealing applications (e.g., gas inlets, chamber lid seals, slit valve doors). A maximum continuous service temperature of 300 °C is suggested. Ultrapure post-cleaning and packaging is standard for all parts made of Kalrez[®] 8575.

Key Performance Features Contribute to Extended Seal Life

- Excellent resistance to oxygen and fluorine-based plasmas, as well as chlorinated cleaning gasses (e.g., CIF₃)
- Very low weight loss in reactive plasmas
- · Very low outgassing properties
- Excellent (low) compression set properties
- · Excellent elastic recovery properties

Suggested Applications

- Chamber lids
- · Gas inlets
- Quartz windows
- Throttle valves
- Other plasma applications

Typical Physical Properties ¹			
Color	White		
Hardness, Shore A (pellet) ²	62		
Hardness, Shore M (O-ring) ³	72		
100% Modulus ⁴ , MPa	2.47		
Tensile Strength at Break ⁴ , MPa	12.04		
Elongation at Break ⁴ , %	230		
Compression Set ⁵ , %, 70 hr at 204 $^{\circ}$ C	29		
Max. Continuous Service Temperature ⁶ , °C	300		

¹ Not to be used for specification purposes

² ASTM D2240 (pellet test specimens)

³ ASTM D2240 and ASTM D1414 (AS568 K214 O-ring test specimens)

⁴ ASTM D412 test method (dumbbell test specimens)

⁵ ASTM D395B (pellet test specimens)

⁶ DuPont proprietary test method

Fabs Choose Kalrez[®] 8575 for Improved Performance

Kalrez[®] 8575 has been reported to significantly improve wafer production in semiconductor etching and ashing applications. In evaluations by a fabline customer, Kalrez[®] 8575 exhibited longer seal life compared to a competitive perfluoroelastomer in both dynamic and static sealing applications.



Case Report #1	
Customer	U.S. East Coast Fabline
Equipment	TEL Unity
Process Type	Deep Trench Etch
Components	End Point Window Seal (229 O-ring) (most difficult location for seal performance)
Process Gasses	HBr, O ₂ , SF ₆ , NF ₃
Rf Power	1500 Watts
Process Temperature	~70 °C
Incumbent Material	Competitive FFKM A2
Incumbent Performance	After 6 months, fluoroelastomer was half eroded, competitive FFKM became brittle, developed cracks and leaked
DuPont [™] Kalrez [®] 8575 Performance:	Evaluated in application for over 10 months without failure Based upon this success, customer evaluated complete seal set (15 sizes) and has changed all competitive FFKM to DuPont [™] Kalrez [®] 8575

Visit us at kalrez.dupont.com or vespel.dupont.com

Contact DuPont at the following regional locations:

North America	Latin America	Europe, Middle East, Africa
800-222-8377	+0800 17 17 15	+41 22 717 51 11
Greater China	ASEAN	Japan
+86-400-8851-888	+65-6586-3688	+81-3-5521-8484

The information set forth herein is furnished free of charge and is based on technical data that DuPont believes to be reliable and falls within the normal range of properties. It is intended for use by persons having technical skill, at their own discretion and risk. This data should not be used to establish specification limits nor used alone as the basis of design. Handling precaution information is given with the understanding that those using it will satisfy themselves that their particular conditions of use present no health or safety hazards. Since conditions of product use and disposal are outside our control, we make no warranties, express or implied, and assume no liability in connection with any use of this information. As with any product, evaluation under end-use conditions prior to specification is essential. Nothing herein is to be taken as a license to operate or a recommendation to infringe on patents.

Caution: Do not use in medical applications involving permanent implantation in the human body. For other medical applications, discuss with your DuPont customer service representative and read Medical Caution Statement H-50103-3.

Copyright © 2010 DuPont. The DuPont Oval Logo, DuPont[™], The miracles of science[™], Kalrez[®], Kalrez[®] and Vespel[®] are trademarks or registered trademarks of E.I. du Pont de Nemours and Company or its affiliates. All rights reserved.

(06/05) Reference No. KZE-H88213-00-I0611

